

BEST AVAILABLE COPY

PCT/IB04/50624 030516



Europäisches
Patentamt

European
Patent Office

Office européen
des brevets

Bescheinigung . Certificate

Attestation

Die angehefteten Unterla-
gen stimmen mit der
ursprünglich eingereichten
Fassung der auf dem näch-
sten Blatt bezeichneten
europäischen Patentanmel-
dung überein.


The attached documents
are exact copies of the
European patent application
described on the following
page, as originally filed.

Les documents fixés à
cette attestation sont
conformes à la version
initialement déposée de
la demande de brevet
européen spécifiée à la
page suivante.

Patentanmeldung Nr. Patent application No. Demande de brevet n°

03101346.9

PRIORITY DOCUMENT
SUBMITTED OR TRANSMITTED IN
COMPLIANCE WITH
RULE 17.1(a) OR (b)



Der Präsident des Europäischen Patentamts;
Im Auftrag

For the President of the European Patent Office

Le Président de l'Office européen des brevets
p.o.

R C van Dijk



Europäisches
Patentamt.

European
Patent Office

Office européen
des brevets

Anmeldung Nr:
Application no.: 03101346.9
Demande no:

Anmeldetag:
Date of filing: 14.05.03
Date de dépôt:

Anmelder/Applicant(s)/Demandeur(s):

Koninklijke Philips Electronics N.V.
Groenewoudseweg 1
5621 BA Eindhoven
PAYS-BAS

Bezeichnung der Erfindung/Title of the invention/Titre de l'invention:
(Falls die Bezeichnung der Erfindung nicht angegeben ist, siehe Beschreibung.
If no title is shown please refer to the description.
Si aucun titre n'est indiqué se référer à la description.)

Method for producing a plurality of bodies

In Anspruch genommene Priorität(en) / Priority(ies) claimed /Priorité(s)
revendiquée(s)

Staat/Tag/Aktenzeichen/State/Date/File no./Pays/Date/Numéro de dépôt:

Internationale Patentklassifikation/International Patent Classification/
Classification internationale des brevets:

G11B7/00

Am Anmeldetag benannte Vertragstaaten/Contracting states designated at date of
filing/Etats contractants désignées lors du dépôt:

AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HU IE IT LU MC NL
PT RO SE SI SK TR LI

Method for producing a plurality of bodies

5 The invention relates to a method for producing a plurality of bodies, each body bearing an optical structure, the optical structures being substantially equal, being associated to a respective information carrier for containing user-information, and being indicative of characteristic information for providing access to the user-information.

10 Such a method is known from EP-A-0 989 553. In this method the information carrier is an optical disk, and the characteristic information is recorded as mechanical embossed pits that are made on the disk, as the body, by using a strong on/off-switched laser light to change the reflectivity of the disk by either changing the composition of or destroying the disk in a minute region thereof, and such a method is not applicable by the end-user. According to said EP-A-0 989 553 the user-information present on a disk is encrypted and the encryption key can be derived from the characteristic information which is pre-recorded on the disk. A player for disks of this type is consequently adapted in order to identify said characteristic information present on a disk, to derive from it the encryption key, and to 15 decrypt the user-information recorded on the disk. A recorder attempting to clone an original disk, i.e. to duplicate the user-information contained in an original disk on a second disk, will not be able to record onto the second disk also the characteristic information, like the one present on the original disk, necessary to decrypt the user-information. As a consequence the 20 user-information contained in the second disk cannot be decrypted and played.

25 With the method described in said EP-A-0 989 553 it is still possible to clone disks, by copying either the content and the characteristic information: in fact, although the equipment necessary to record characteristic information on a disk is unlikely to be easily available to an end-user, such an equipment is available to professional counterfeiters. It is a disadvantage of the known method that the products produced can be cloned when professional equipment is employed.

It is an object of the invention to provide a method of the kind described in the opening paragraph, by which are produced bodies bearing optical structures, which are substantially impossible to be cloned, and which method nevertheless allows for the production of a plurality of bodies bearing substantially identical optical structures.

5 This object is achieved by:

- producing a stamp by attaching particles to a surface of an auxiliary body; and
- using the stamp to imprint an imprintable material, thereby producing the plurality of bodies, the each body having at least a surface portion bearing an imprint of the stamp.

10 The result of the method is a plurality of bodies, each body bearing an imprint of the stamp; the imprint is the optical structure indicative of characteristic information. An optical structure is a surface portion of a body which if irradiated with a coherent beam of light gives rise to reflection, refraction or diffraction of the light, or a combination of two or three thereof. With a screen positioned in an adequate position in respect with the light source
15 and the optical structure, it is possible to observe on the screen a speckle pattern due to the interaction of the light with the optical structure. The observed speckle pattern depends on the parameters defining the coherent beam of light, like for example wavelength and phase, and on the internal microstructure of the optical structure, i.e. on the shape of the imprint. The speckle pattern can be sensed with a sensor and can be further processed in order to
20 derive from it the characteristic information. In general, the characteristic information is whatever information necessary to access the user-information. e.g. a decryption key for decrypting encrypted user-information.

A player for an information carrier of the type referred to in the method of the invention will consequently be adapted to identify from the associated optical structure the
25 characteristic information, and to use said characteristic information to access the user-information present on the information carrier.

However, the information carrier referred to in the method of the invention does not need to actually contain user-information, but it can also be an information carrier of recordable type. A recorder for such a recordable information carrier will consequently be
30 adapted to identify from the associated optical structure the characteristic information, to use said characteristic information to encode accordingly the user-information to be recorded, and to record the encoded user-information.

The usage of a stamp is to guarantee the reproducibility: in fact, the producer or the owner of the stamp has the possibility to reproduce substantially equal optical

structures a plurality of times. Reproducibility is an important requirement for the industrial applicability, since characteristic information is to be derived from the optical structure. If the optical structure was not reproducible, every optical structure would be unique and two optical structures would indicate different characteristic information. Hence, in the case that the characteristic information comprises an encryption/decryption key, also the encryption/decryption key would be different, and different would be the encrypted user-information: in this way every disk should be mastered individually, implying a complex, expensive and unrealistic mastering process.

By the method of the invention however, a plurality of bodies bearing substantially identical optical structures indicative of identical characteristic information is produced.

What makes an optical structure substantially impossible to clone is the way the characteristic information is derived from it together with the way the optical structure is produced. The speckle pattern, and consequently the characteristic information, can be seen as the output of a physical One-Way Function (OWF), the inputs of which are the internal microstructure of the optical structure and the irradiating beam of light. An OWF is a function easy to evaluate in the forward sense, but generally unfeasible to compute in the reverse direction, and wherein the output domain is very large and the input domain is even much larger. An attempt to clone an optical structure could be based on its physical observation, or on its behavioral observation. An optical structure could in principle be observed with a noninvasive tomographic imaging technique, however equipment presently available does not allow for the microfabrication of the internal microstructure to the required level of detail. The possibility to deduce the internal microstructure of the optical structure, based on its behavior, i.e. speckle pattern and characteristic information as a response to a given irradiating beam is ruled out due to the properties of an OWF.

The possibility to produce an optical structure, potentially different from the original one, but having exactly the same behavior is also unfeasible, given the large number of possible values for the parameters defining the coherent beam of light, and the computational complexity of reconstructing an optical structure having a known behavior.

Further detailed considerations on the properties of physical OWF, and on the substantial impossibility to clone an optical structure, or to reconstruct an optical structure with a known behavior, or even to fool a system for access control of user-information based on optical structure are brought in the article "Physical One-Way Functions" Ravikanth Pappu et al., Vol. 297 SCIENCE, 20/09/2002.

The method of the invention can be extended to comprise a further step of applying onto the imprint of the each body a layer of reflecting material having a surface facing away from the imprint which substantially follows the imprint.

5 In this way a reflective layer is applied, the aim of which is enhancing the reflectivity of the optical structure. This implies that the screen which has to sense the speckle pattern has to be positioned as facing the surface bearing the imprint: as a consequence, both the laser for irradiating the optical structure and the screen for sensing the speckle pattern will be positioned on the same side of the body.

10 The method of the invention can be extended to comprise the following further steps:

- applying over the imprint of the each body a layer of an other, substantially transparent, imprintable material;
- using the stamp an additional time to imprint the layer of the other imprintable material, thereby making an additional imprint on the each body.

15 The application of the other imprintable material is to prepare the body to receive an additional imprint. The layer of the other imprintable material can be applied over the layer of reflective material, if this is present, or directly over the surface or surface portion bearing the first imprint. The additional imprint is then produced with the same stamp on the layer of the other imprintable material, thereby obtaining a dual-layer optical structure, more complex than an optical structure with a single imprint, and thus even more difficult to
20 clone. The layer of the other imprintable material needs to be substantially transparent, otherwise the first imprint would not adequately contribute to interaction with light when irradiated.

25 The method of the invention can be extended to comprise the following further steps:

- producing an additional stamp by attaching particles to a surface of an additional auxiliary body;
- applying over the imprint of the each body a layer of an other, substantially transparent, imprintable material;
- 30 - using the additional stamp to imprint the layer of the other imprintable material, thereby making an additional imprint on the each body.

The application of the other imprintable material is to prepare the body to receive an additional imprint. The layer of the other imprintable material can be applied over the layer of reflective material, if this is present, or directly over the surface or surface

portion bearing the first imprint. The additional imprint is then produced with the additional stamp, which has been prepared for this purpose, on the layer of the other imprintable material, thereby obtaining a dual-layer optical structure, more complex than an optical structure with a single imprint, and thus even more difficult to clone. The layer of other
5 imprintable material needs to be substantially transparent, otherwise the first imprint would not adequately contribute to interaction with light when irradiated.

When an additional imprint is made, preferably the imprintable material used has a first refractive index, and the other imprintable material has a second refractive index, the second refractive index being different from the first refractive index.

10 This feature may be desirable when no interposition material is present between the first imprint and the layer of the other imprintable material, in order to make sure that the interface between the two adequately contributes to interaction with light when irradiated.

15 In view of making an additional imprint, the method of the invention can be extended by interposing between the imprint and the layer of the other imprintable material of the each body a substantially transparent separation layer.

In fact, the application of the other imprintable material may be preceded by the application of an separation layer. This step may be desirable, for example, when the other imprintable material is not suitable for covering the first imprint and filling the recesses
20 thereof. The separation layer needs to be substantially transparent, otherwise the first imprint would not adequately contribute to interaction with light when irradiated. The presence of a separation layer allows the use of the same material as imprintable material and other imprintable material.

25 When the separation layer is present, preferably the imprintable material used has a first refractive index, and the separation layer has a third refractive index, the third refractive index being different from the first refractive index.

This feature may be desirable when no reflective layer is present between the first imprint and the separation layer, in order to make sure that the interface between the two adequately contributes to interaction with light when irradiated.

30 In order to protect the optical structure, the method of the invention can be extended by applying on the imprint of the each body a substantially transparent covering layer.

The purpose is to protect the imprint from any mechanical alteration, for example due to manipulation of the body, which may consequently alter the optical structure

as a whole. The covering layer needs to be substantially transparent. Moreover, when the covering layer is present, preferably the material used as imprintable material has a first

refractive index, and covering layer has a fourth refractive index, the fourth refractive index being different from the first refractive index. If the optical structure is a double-layer or a multi-layer optical structure, the covering layer can be applied on the uppermost imprint.

According to another aspect of the method of the invention, the each body is a laminated body comprising a reflective layer.

The presence of a reflective layer is aimed at enhancing the reflectivity of the optical structure and implies that the screen which has to sense the speckle pattern has to be positioned as facing the surface bearing the imprint: as a consequence, both the laser for irradiating the optical structure and the screen for sensing the speckle pattern will be positioned on the same side of the body.

According to another aspect of the method of the invention, the each body is integral with the respective information carrier. In other words, the information carrier itself is used as body for bearing the optical structure.

The optical structure is associated to a respective information carrier for containing user-information. The information carrier can be, for example, an optical disk.

According to another aspect of the method of the invention, particles of diamond are used as the particles.

In order to make sure that the imprint can be reproduced substantially equal by a large number of times, the particles used to produce the stamp and, occasionally, the additional stamp are preferably solid particles of a hard material, like for example diamond or tungsten carbide, so that repetitive usage of the stamp for the large number of times does not wear out the shape of the stamp.

According to another aspect of the method of the invention, particles having a size range between 100 nm and 1 micron are used as the particles.

The usage of particles in this size range is to make sure that diffractive effects resulting from the irradiation of the optical structure due to recesses in the imprint and, occasionally, in the additional imprint are adequately exploited for the formation of the speckle pattern.

The already cited article "Physical One-Way Functions", proposes the use of inhomogeneous structures in a system for access control of user-information contained in an information carrier, for example a credit card. The inhomogeneous structures are used to generate characteristic information that is checked against control information contained in

the information carrier in order to authenticate the information carrier. Said article however fails to provide a method for the production of inhomogeneous structures, and in particular of substantially equal inhomogeneous structures, which problem is recognized when attempting to apply a similar system for access control, for example, to pre-recorded optical disks.

5

These and other aspects of the invention will be further elucidated and described with reference to the drawings.

Fig. 1 displays a cross-section of a stamp and a cross-section of a body bearing an imprint of the stamp,

Fig. 2 displays a cross-section of a body bearing an optical structure, across the optical structure, in different conditions,

Fig. 3 displays an additional stamp and a cross-section of a body bearing a dual-layer optical structure, across the optical structure, in different conditions,

Fig. 4 displays an optical disk bearing an optical structure, and a cross-section of it,

Fig. 5 displays a system for access control of user-information contained in an optical disk, based on an optical structure indicative of characteristic information.

20

Fig. 1 displays a cross-section of a stamp and a cross-section of a body bearing an imprint of the stamp.

In the Figure it is possible to see a stamp 13, and in particular particles 14 attached to a surface 15 of an auxiliary body 16, a body 10 bearing an imprint 11 of the stamp 13, and in particular recesses 12 in the imprint 11 due to the particles 14 attached to the auxiliary body 16. The imprint 11 of the stamp 13 is an optical structure.

According to the method of the invention a plurality of bodies are produced, where each body 10 is associated to a respective information carrier for containing user-information and is bearing a substantially equal optical structure indicative of characteristic information necessary to access the user-information present in the respective information carrier.

30

In the first step a stamp 13 is produced, by attaching particles 14 to a surface 15 of an auxiliary body 16.

The stamp 13 can be obtained, for example, by applying a gluing material 17 onto the surface 15 of the auxiliary body 16, distributing some particles 14, for example randomly, onto the surface 15, and solidifying the gluing material 17.

In order to make sure that the imprint can be reproduced substantially equal by a large number of times, the used particles are preferably solid particles of a hard material, like for example tungsten carbide or diamond, so that repetitive usage of the stamp for the large number of times does not wear out the shape of the stamp. Preferably, the used particles have a size range of the same order of magnitude of the wavelength of the irradiated light, so for example 100 nm-1 micron.

In the second step, the stamp 13 is used to imprint an imprintable material, thereby producing the plurality of bodies, the each body 10 having at least a surface portion bearing an imprint 11 of the stamp 13.

The second step can be accomplished, for example, by using the stamp on a plurality of pre-existing bodies, not having any imprint of the stamp yet, to produce an imprint on each of these pre-existing bodies, for example by a molding process. The imprint thereby produced on a surface portion is the optical structure. A plurality of optical structures produced with the same stamp is substantially equal, and thus indicative of the same characteristic information. As an alternative, the second step could be accomplished starting from a shapeless material, the body being formed at the same time when a surface portion of it is shaped by the stamp.

In the case that pre-existing bodies, not having any imprint of the stamp yet, are employed, the imprint may be produced on a surface portion of the pre-existing body that is imprintable: this can simply be for example the material of which consists the pre-existing body, or a surface portion of it; alternatively, the surface portion of the pre-existing body that is imprintable can be obtained by applying an initial layer of imprintable material. As imprintable material can be used for example polycarbonate, epoxy or diacryl.

Fig. 2 displays a cross-section of a body bearing an optical structure, across the optical structure, in different conditions.

In Fig. 2a it is possible to see a body 10, an imprint 11 as the optical structure, and a transparent covering layer 20 over the imprint 11. The covering layer 20 is covering the imprint 11 and filling the recesses 12 thereof.

The purpose of the covering layer 20 is to protect the imprint 11 from any mechanical alteration, for example due to manipulation of the body 10, which may consequently alter the optical structure as a whole.

In Fig. 2b, in addition to the items present in Fig. 2a, it is possible to see also a pre-existing reflective layer 21.

In the case that pre-existing bodies, not having any imprint of the stamp yet, are employed as bodies where the imprint of the stamp is made, said pre-existing bodies may be laminated pre-existing bodies, comprising a pre-existing reflective layer. As anticipated, the light resulting from the interaction of the irradiated beam with the optical structure produces a speckle pattern on a screen. The presence of a reflective material under the imprint implies that the screen which has to sense the speckle pattern has to be positioned as facing the surface bearing the imprint: as a consequence, both the laser for irradiating the optical structure and the screen for sensing the speckle pattern will be positioned on the same side of the body.

In Fig. 2c, in addition to the items present in Fig. 2a, it is possible to see also an applied reflective layer 22, and its surface 23 facing away from the imprint 11 which substantially follows the imprint 11.

When the body 10 does not comprise also a pre-existing reflective layer 21, it can be useful to apply a layer 22 of reflective material over the first imprint 11. In this case the applied reflective layer 22 has the same implications and advantages of the previously described pre-existing reflective layer 21.

However the presence of a reflective layer anywhere is not mandatory, and in the case that there is no reflective layer the screen for sensing the speckle pattern is preferably positioned on a side of the body other than the one from which the optical structure is irradiated, provided that the body is substantially transparent.

Fig. 3 displays an additional stamp and a cross-section of a body bearing a dual-layer optical structure, across the optical structure, in different conditions.

In Fig. 3a it is possible to see an additional stamp 13', and in particular particles 14' attached to a surface 15' of an additional auxiliary body 16'.

In Fig. 3b it is possible to see a body 10, an optional pre-existing reflective layer 21, a first imprint 11, an optional applied reflective layer 22, a layer of an other imprintable material 30, an additional imprint 31 made on the layer of the other imprintable material 30, and a covering layer 20 over the additional imprint 31. The covering layer 20 is covering the additional imprint 31 and filling the recesses thereof.

The purpose of the covering layer 20 is to protect the uppermost imprint from any mechanical alteration, for example due to manipulation of the body 10, which may consequently alter the optical structure as a whole.

In the case that no interposition material is present between the first imprint 11 and the layer of the other imprintable material 30, it is desirable to use materials with different refractive indexes as imprintable material and other imprintable material 30, in order to make sure that the interface between the two adequately contributes to interaction with light when irradiated. The presence of a reflective layer 22 between the first imprint 11 and the layer of other imprintable material 30, allows for the use of the same material as imprintable material and other imprintable material 30.

The additional imprint 31 can be obtained with an additional stamp 13' as well as with the first stamp 13. The purpose of making an additional imprint 31 is to obtain a dual-layer optical structure, more complex than an optical structure with a single imprint, and thus even more difficult to clone. To this end, preferably the additional imprint 31 is substantially superimposed to the first imprint 11, however it can also be partly superimposed or not at all superimposed. Furthermore, in the case that the additional imprint 31 is substantially superimposed to the first imprint 11 and that additional imprint 31 is made with the same stamp 13, the stamp 13 is preferably rotated over a chosen angle in respect with the first time it was used.

In order to obtain even more complex optical structures it is possible to produce even further imprints on even further layers, thereby obtaining multi-layer optical structures. Moreover, it is possible to produce some of the even further imprints with even further stamps, and some of the even further imprints with stamps already used, thereby combining the two techniques described to produce additional imprints.

In Fig. 3c, in addition to the items present in Fig. 3a, it is possible to see also an interposition layer 32.

Also in this case, the presence of an interposition layer 32 allows for the use of the same material as imprintable material and other imprintable material 30.

The presence of an interposition layer 32 and the presence of an applied reflective layer 22 are not mutually exclusive, but can also be combined.

Fig. 4 displays an optical disk bearing an optical structure, and a cross-section of it.

In Fig. 4a it is possible to see the optical disk 40, and in particular an imprint 11, present on a surface portion of it, as an optical structure.

Fig. 4b displays a portion of a cross-section of the optical disk 40 shown in Fig. 4a across the imprint 11. It is possible to see an information layer 42, an optional pre-existing reflective layer 21, the imprint 11, and a covering layer 20. In this case, the body 10

bearing the optical structure is the respective information carrier to which the optical structure is associated, and the information carrier is an optical disk 40. The optical structure can be present in the substrate of the disk, and can be observed from a side of the disk.

5 The optical structure can be superimposed to the information layer, or be present in a portion of the disk where there is no information layer, like for example at the inner side of the disk. However, other alternatives are possible as the body bearing the optical structure: for example the case of the disk, if the disk is contained in a case, or the cartridge of the disk, if the disk is permanently incorporated in a cartridge, or a separate body accompanying the disk, like for example a card.

10 In said above circumstance, in which the bodies bearing the optical structures are the information carriers themselves and the information carriers are optical disks, if in particular the optical disks are pre-recorded optical disks carrying the same user-information, for example a given music album or a given film, the production of the plurality of disks may comprise the following steps: after the stamp or the stamps are obtained, an optical structure
15 is produced; then the characteristic information indicated by the optical structure is identified; then the user-information is encoded according to the identified characteristic information; eventually the plurality of disks is produced, the disks carrying the encoded user-information and bearing the optical structures, the optical structures being substantially equal to the first one, since they are produced with the stamp or stamps.

20 A player for a disk of the type displayed in Figure 4 will consequently be adapted to identify from the optical structure the characteristic information, and to use said characteristic information to access the user-information present on the disk. Furthermore, a disk of the type displayed in the Figure 4 does not need to be a pre-recorded disk, nor to actually contain user-information, but it can also be a disk of recordable type. A recorder for
25 such a disk will consequently be adapted to identify from the associated optical structure the characteristic information, and to use said characteristic information to encode accordingly the user-information to be recorded, and to record the encoded user-information onto the disk.

30 As background information, Fig. 5 displays a system for access control of user-information contained in an optical disk, based on an optical structure indicative of characteristic information, for the general understanding of how such a system operates.

In the Figure it is possible to see a laser 502, a coherent beam of light 503 produced by the laser 502, an optical disk 40, an imprint 11 as an optical structure borne by the optical disk 40, a screen 506, a speckle pattern 505 produced on the screen 506, a sensed

speckle pattern 507, a digital filter 508, a filtered speckle pattern 509, a mathematical OWF 510, a characteristic information 511, reading means 500, encoded user-information 501, an access-control-block 512, and decoded user-information.

5 The laser 502 irradiates with a coherent beam of light 503 the imprint 11, as the optical structure borne by an optical disk 40. The light resulting from the interaction of the irradiated beam 503 with the optical structure produces the speckle pattern 505 on the screen 506.

10 The observed speckle pattern depends on the parameters defining the coherent beam of light, like for example wavelength and phase, and on the internal microstructure of the optical structure, i.e. on the shape of the imprint or imprints. Parameters like for example the wavelength of the beam can be variable: preferably, the wavelength will vary around the size range of the recesses present in the imprint, so for example 100 nm-1 micron. The position and/or orientation of the laser may also be variable within certain ranges, if mechanical means supporting the laser provide for this possibility.

15 The speckle pattern 505 is sensed by the screen 506 and converted into digital information representing the sensed speckle pattern 507. A digital filter 508 is then applied to the sensed speckle pattern 507, in order to make the characteristic information not sensitive to microscopic differences between imprints obtained with the same stamp, and due for example to the production process, or to environmental alterations, or to the presence of fingerprints, while keeping sufficient sensitivity to detect counterfeited optical structures. The applied filter can be, for example, a two-dimensional Gabor transform. A further, mathematical, OWF 510 is applied to the filtered speckle pattern 509, to obtain the characteristic information 511. The used mathematical OWF 510 can be, for example, a simple hashing function compressing the filtered speckle pattern 509 to a relatively short string of bits.

25 Reading means 500 yield the encoded user-information 501 present on the optical disk 40, the access control block 512 can decode the encoded user-information 501, as the correct characteristic information 511 is provided, and eventually the decoded user-information 513 is made available.

30 The characteristic information 511 may consist, for example, of an encryption/decryption key: consequently the encoded user-information is user-information encrypted according to that key and the access control block uses the key to decrypt the user-information. As an alternative, the user-information could be encapsulated in a software object requiring an access key to be accessed, the characteristic information 511 may consist

of the required access key, and the access control block may consequently use the access key to access the software object. Preferably, the used access control will comprise both the above techniques, and the characteristic information 511 will be structured accordingly, the characteristic information 511 being whatever information is necessary to access the user-
5 information. The characteristic information 511 may be derived not only from a single irradiation of the optical structure but from several irradiations produced with different values of the parameters controlling the beam.

Although the invention has been elucidated with reference to the embodiments described above, it will be evident that other embodiments may be alternatively used to
10 achieve the same object. The scope of the invention is therefore not limited to the embodiments described above, but can also be applied to a stamp having a more complex relief structure than the one simply obtained by attaching particles to a surface of it.

It must further be noted that the term "comprises/comprising" when used in this specification, including the claims, is taken to specify the presence of stated features,
15 integers, steps or components, but does not exclude the presence or addition of one or more other features, integers, steps, components or groups thereof. It must also be noted that the word "a" or "an" preceding an element in a claim does not exclude the presence of a plurality of such elements. Moreover, any reference signs do not limit the scope of the claims; the invention can be implemented by means of both hardware and software, and several "means"
20 may be represented by the same item of hardware. Furthermore, the invention resides in each and every novel feature or combination of features.

The invention can be summarized as follows: in the described method for producing a plurality of bodies bearing equal imprints of a stamp as optical structures a stamp
13 is initially produced, by attaching particles 14 to a surface 15 of an auxiliary body 16;
25 then, the stamp 13 is used to produce an imprint 11 on a plurality of bodies 10. Optical structures can be irradiated, producing on a screen a speckle pattern indicative of a key. It is substantially impossible to clone a given optical structure with current technological means. Optical structures represent physical One Way Functions, easy to compute in the forward sense but unfeasible to reverse. Thus, they can be used to build an access/copy protection
30 system of user-information contained in an information carrier associated to the body 10. The reproducibility of the optical structures makes this method suitable for optical disks.

CLAIMS:

1. A method for producing a plurality of bodies, each body (10) bearing an optical structure, the optical structures being substantially equal, being associated to a respective information carrier for containing user-information, and being indicative of characteristic information for providing access to the user-information, characterized by:

- 5 - producing a stamp (13) by attaching particles (14) to a surface (15) of an auxiliary body (16); and
- using the stamp (13) to imprint an imprintable material, thereby producing the plurality of bodies, the each body (10) having at least a surface portion bearing an imprint (11) of the stamp (13).

10 2. A method as claimed in claim 1, characterized by applying onto the imprint (11) of the each body (10) a layer of reflecting material (22) having a surface (23) facing away from the imprint (11) which substantially follows the imprint (11).

15 3. A method as claimed in claim 1 or 2, characterized by:

- applying over the imprint (11) of the each body (10) a layer of an other, substantially transparent, imprintable material (30);

- using the stamp (13) an additional time to imprint the layer of the other imprintable material (30), thereby making an additional imprint (31) on the each body (10).

20 4. A method as claimed in claim 1 or 2, characterized by:

- producing an additional stamp (13') by attaching particles (14') to a surface (15') of an additional auxiliary body (16'); and

- applying over the imprint (11) of the each body (10) a layer of an other, substantially transparent, imprintable material (30);

25 - using the additional stamp (13') to imprint the layer of the other imprintable material (30), thereby making an additional imprint (31) on the each body (10).

5. A method as claimed in claims 3 or 4, characterized in that the imprintable material used has a first refractive index, and the other imprintable material (30) has a second refractive index, the second refractive index being different from the first refractive index.
- 5 6. A method as claimed in claims 3 or 4, characterized by interposing between the imprint (11) and the layer of the other imprintable material (30) of the each body (10) a substantially transparent separation layer (32).
- 10 7. A method as claimed in claim 6, characterized in that the imprintable material used has a first refractive index, and the separation layer (32) has a third refractive index, the third refractive index being different from the first refractive index.
- 15 8. A method as claimed in claim 1, characterized by applying over the imprint (11) of the each body (10) a substantially transparent covering layer (20).
9. A method as claimed in claim 1, characterized in that the each body (10) is a laminated body comprising a reflective layer (21).
- 20 10. A method as claimed in claim 1, characterized in that the each body (10) is integral with the respective information carrier (40).
11. A method as claimed in claim 1 or 4, characterized in that particles of diamond are used as the particles (14).
- 25 12. A method as claimed in claim 1 or 4, characterized in that particles having a size range between 100 nm and 1 micron are used as the particles (14).

ABSTRACT:

In the described method for producing a plurality of bodies bearing equal imprints of a stamp as optical structures a stamp (13) is initially produced, by attaching particles (14) to a surface (15) of an auxiliary body (16); then, the stamp (13) is used to produce an imprint (11) on a plurality of bodies (10). Optical structures can be irradiated, producing on a screen a speckle pattern indicative of a key. It is substantially impossible to clone a given optical structure with current technological means. Optical structures represent physical One Way Functions, easy to compute in the forward sense but unfeasible to reverse. Thus, they can be used to build an access/copy protection system of user-information contained in an information carrier associated to the body 10. The reproducibility of the optical structures makes this method suitable for optical disks.

Fig. 1




FIG. 2a




FIG. 2b




FIG. 2c

3/5




FIG. 3a




FIG. 3b




FIG. 3c




FIG. 4a




FIG. 4b




FIG. 5

PCT/IB2004/050624



**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☐ FADED TEXT OR DRAWING
- ☒ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☒ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.